

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-174304

(43)Date of publication of application : 08.07.1997

(51)Int.Cl. B23B 27/14
C23C 16/32
C23C 16/34
C23C 16/36
C23C 16/40
C23C 16/52
// B23P 15/28

(21)Application number : 07-336644

(71)Applicant : MITSUBISHI MATERIALS CORP


(22)Date of filing : 25.12.1995

(72)Inventor : YAMADA HISASHI

(54) SURFACE COATED CEMENTED CARBIDE-MADE CUTTING TOOL EXCELLENT IN PITCHING RESISTANCE**(57)Abstract:**

PROBLEM TO BE SOLVED: To provide a surface coated cemented carbide cutting tool excellent in pitching resistance.

SOLUTION: This cutting tool is constituted so that a hard coating layer composed of an inside layer composed of one kind of single layer or two or more kinds of plural layers among a TiC layer, a TiN layer and a TiCN layer, an intermediate layer composed of a TiCO layer and/or a TiCNO layer and an outside layer composed of Al₂O₃ is formed in an average layer thickness of 5 to 20μm on a surface of a WC group cemented carbide base body. In this case, an interface part with an Al₂O₃ layer in the intermediate layer is formed as a sharpened needle crystal structure.

**LEGAL STATUS**

[Date of request for examination]

29.09.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

BEST AVAILABLE COPY

[Patent number] 3250134
[Date of registration] 16.11.2001
[Number of appeal against examiner's decision of rejection]
[Date of requesting appeal against examiner's decision of rejection]
[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office